

C03 CALCE PULITA



Protective oil water repellent coating

Code: 670T0001000

Up-dated: 05/03/2015

Print date: 16/03/2018

Revision n°: 5



Proprieties: *Transpiring*
 Good consolidating power
 oil water repellent

VOC *Primer fixture*
(Directive 2004/42/CE) *Limit value for C03 Calce Pulita (Cat. A / H): 750 g/l*
 C03 Calce Pulita contains maximum 750 g/l di VOC.

Support Preparation: *On new stone supports: be sure that the support is cohesive and clean.*
 On old stone supports: eliminate any traces of dust or soluble salts with hydro
 washer at high temperatures (85 °C).
 On supports that have been attacked by algae or moulds: clean the walls with
 Sterilene leaving to act for 24/36 hours after which rising with hydro washer at
 high temperatures (85 °C).

Support Preparation: *On an adequately prepared support, apply Calce Pulita by brush or by spray gun at*
 low pressures until total impregnation of the support.

Environmental Conditions at *Room Temperature : min + 5° C max + 35° C*
application: *Support Temperature : min + 5° C max + 35° C*
 Relative humidity : less than 80 %.



Storage:	Store the material in closed containers away from freezing temperatures.
Standard indication:	CO3 CALCE PULITA: protective oil water repellent with consolidating properties for the treatment of stone supports and lime finishes.

Technical Informations

Apperance:	Neutral
Available colours:	Trasparent
Medium Specific Weight:	1,77 kg/l
Application:	by brush or spray gun
Thinning:	ready to use
Theoretical coverage:	0,2 – 0,4 kg / mq. The coverage can vary in function of the characteristics of the support.
Shelf-life:	12 months
Equipment cleaning:	mineral spirits

General instructions

The technical indications given are based on our experience. The correct use of the material implicates that the listed methods of use have been respected, and, in a particular way, the correct preparation of the support. Given the multiply uses of the product and the impossibility to control the application of the coating, it is the customer's exclusive responsibility for the end result of the application.

All the indications described are only indicative, and are not binding and are not bound from a juridical point of view or tied to the supplier contract. Any forms of warranty will be released by our collaborators only after having evaluated the support to be treated and will be attached in writing to the proposed coating cycle.

RIVAL srl

via Rea, 31
36020 Pove del Grappa,
Vicenza, Italia

T +39 (0424) 808 241.2 r.a.
F +39 (0424) 808 955

info@rivalspa.com
www.rivalspa.com

Cap. soc. € 100.000,00 i.v.
(a socio unico)
P.I. IT 00171370240
R.I./C.F. VI 00171370240
Posizione Expert M./VI 022843
R.E.A. 106704 VI

Società Unipersonale
soggetta alla direzione
e coordinamento del
Colorificio Sammarinese SpA