

Products	mixing ratio	N° layers	Tools	Drying time
Decofix or Wall2Floor Primer	Decofix 50 - 100% with water / 0.5 l comp A + 0.25 l comp B + 3 l water	one	Brush/roller	3-4 h
Wall2Floor Epoxy Binder + Wall2Floor Rasal	1.6 l comp A + 0.8 comp B + 3 - 3.5 l water + 25 kg W2F Rasal	two	Stainless steel trowel	3-4 h
Wall2Floor Top Coat Waterproof	20 kg comp A + 1.2 kg comp B (no add water)	two	Stainless steel trowel	3-4 h first layer 12-14 h second layer
Mineral Sealer	0,5 l comp A + 0.35 l comp B + 2.1 - 2.5 l water	one	brush	3-4 h
Wall2Floor Clear Finish Countertop Protection (Satin)	2.5 l comp A + 0.75 l comp B + 0 - 10% water	two	Medium hair roller	4-6 h first layer 24 h second layer 7 days

For all the two-components products, mix together comp A + comp B before any application, dilution, mixing

To prepare the substrate choose between Decofix or wall2Floor Primer. If the screed is compact Decofix; if the surface is chalking Wall2Floor Primer. Wall2Floor Primer is stronger and deeper consolidator than the Decofix.

It is recommended to apply Mineral Sealer in wet areas, especially when the top coat has been sanded.

For the final protection my favorite is Satin, but if you need Matt I recommend applying one coat (the first) of Satin or Glossy and the second Matt/Ultra Matt. 7 days of drying for the final performances and before surface cleaning